

DUCALE PITTURA

Cod. 752.2.001

BuildingLine – pitture minerali

DUCALE PITTURA è un prodotto a base di grassello di calce a lunga stagionatura e cariche minerali naturali. La composizione naturale conferisce un'eccezionale traspirabilità, una bassissima ritenzione dello smog e un'efficace resistenza agli attacchi batterici. Queste caratteristiche consentono l'impiego di *DUCALE PITTURA* quale rivestimento per il restauro di edifici storici e per la decorazione di facciate e interni di prestigio.

BuildingLine – mineral paints

DUCALE PITTURA is a product based on well aged lime putty and natural components. Due to its outstanding permeability to water vapor, its very low smog retention and its resistance to bacteria and mildew, it is suitable for finishing in restoring and maintenance works on old buildings and high value interiors, like museums, villas, banks, hotels, offices, etc.

Confezioni di vendita

- 15 L

C.O.V.

- < 20 g/l

Peso specifico

- $1.550 \pm 0.030 \text{ kg/dm}^3$

Aspetto del film essiccato

- Opaco

Colore

- Bianco

Resa pratica

- $7 \div 8 \text{ m}^2/\text{litro}$

Consumo pratico

- $120 \div 140 \text{ ml/m}^2$

Diluyente

- Acqua

Metodo di applicazione

- Pennello

Pack sizes

- 15 litres

V.O.C.

- < 20 g/l

Specific gravity

- $1.550 \pm 0.030 \text{ kg/dm}^3$

Finish

- Flat

Colour range

- White

Practical coverage

- $7 \div 8 \text{ m}^2/\text{litre}$

Practical consumption

- $120 \div 140 \text{ ml/m}^2$

Thinner

- Water

Application

- Brush

Preparazione della superficie

- Tipo di supporto: intonaco civile, intonaco a calce, intonaco a gesso, vecchie pitture minerali.
- Asportare eventuali parti in fase di distacco; su superfici porose o assorbenti è necessario applicare una mano di fissativo ISOFARB-ACR2. Nel caso di superfici con buona solidità è sufficiente togliere la polvere.
- Nel caso di superfici dipinte con idropitture sintetiche, asportare la vecchia pitturazione, spazzolare il supporto e se possibile idrolavare.
- La pitturazione di superfici con efflorescenze saline o soggette a umidità di risalita non garantisce un'adesione durevole e non esclude la formazione di difetti.
- L'uso di coloranti diversi da quelli da noi forniti non garantisce da parte nostra la stabilità della tinta derivata.
- Per le applicazioni all'esterno, proteggere per almeno 4 giorni dalla pioggia battente mediante mascherature
- DUCALE PITTURA è un prodotto caustico: proteggere la pelle e gli occhi dagli spruzzi ed usare guanti in gomma durante l'applicazione

Numero delle mani

- Due - tre

Condizioni di applicazione

- Temperatura: 10-40°C
- Umidità relativa <80%

Dati per l'applicazione

Pennello

- | | | |
|--------------|-------|-------|
| • Diluizione | 30÷40 | % v/v |
|--------------|-------|-------|

Tempi di indurimento a 20°C – 50% U.R.

- | | |
|-----------------|-------|
| • al tatto | 1-2 h |
| • ripitturabile | 5-6 h |

Lavaggio delle attrezzature

- Acqua immediatamente dopo l'uso

Durata a magazzino

- 12 mesi, con T max di 40°C, in latta sigillata, al coperto e al riparo dal gelo.

Poiché le condizioni di impiego dei nostri materiali non sono sotto il nostro controllo, non possiamo che garantire la qualità dei prodotti, quindi non ci assumiamo alcuna responsabilità circa l'uso che dei medesimi viene fatto e circa qualsivoglia danno diretto o indiretto possa derivare a chiunque dal loro impiego. G.FARBEX non dà alcuna garanzia, implicita o esplicita, salvo specifica pattuizione scritta fra le parti.

Surface preparation

- Apply on plaster, lime plaster, gypsum plaster, old mineral paints.
- Remove any loose, flaking and poorly adhering material, using mechanical means. A sealing coat of *ISOFARB ACR2* is recommended, obligatory on very porous and absorbent surfaces. If the surface is sound, simply remove the dust.
- If the surface is painted with emulsion paints, get the old paint off, brush the surface and if necessary wash with water under pressure.
- Coating of surfaces with salt efflorescence or capillary humidity does not guarantee a lasting adhesion and does not exclude defects formation.
- If different colorants are used which we advice from, colour stability is not guaranteed.
- Protect outdoor application from rain for at least 4 days.
- DUCALE PITTURA is a caustic product: during application protect eyes and skin and wear rubber gloves.

Coats

- Two - three

Environmental conditions

- Temperature: 50-120°F
- Relative humidity <80%

Application data

Brush

- | | | |
|------------|-------|-------|
| • Thinning | 30÷40 | % v/v |
|------------|-------|-------|

Drying times at 68°F – 50% R.H.

- | | |
|-------------|-------|
| • to touch | 1-2 h |
| • to recoat | 5-6 h |

Cleaning up

- Water immediately after use

Shelf life

- 12 months, with T max of 100°F, in sealed drum, indoors and protected against freeze.

This product data sheet is based on data believed to be reliable, and are intended for use by personnel having skill and know-how, at their own risk and in accordance with current industry practice and normal operating conditions. Variation in operating conditions and procedures may cause unsatisfactory results. Since we have no control over the conditions of service, we expressly disclaim any responsibility for the results obtained from the use of this product or for any consequential or incidental effects of any kind.