

HYDROLUX

Cod. W18.4.001 – lucido/glossy

Cod. W19.4.001 – opaco/flat

WoodLine - vernici

Vernice poliuretana all'acqua monocomponente per interni ed esterni di grande elasticità e resistenza ai raggi UV e agli agenti atmosferici.

HYDROLUX ha un'ottima durezza superficiale e un'elevata resistenza all'abrasione, non ingiallisce, è facilmente lavabile, non contiene sostanze pericolose per la salute, non ha odore e non è infiammabile.

È raccomandata per la verniciatura di parquet, mobili, sedie, manufatti di legno in genere.

Confezioni di vendita

- 0.750 litri – 5 litri

C.O.V.

- < 60 g/l

Peso specifico

- $1.020 \pm 0.030 \text{ kg/dm}^3$

Aspetto del film essiccato

- Lucido o opaco

Colore

- trasparente

Resa pratica

- $10 \div 12 \text{ m}^2/\text{l}$

Consumo pratico

- $70 \div 100 \text{ ml/m}^2$

Diluyente

- acqua

Metodo di applicazione

- Spruzzo ad aria
- Pennello, rullo

Preparazione della superficie

- Applicare su supporti puliti e asciutti ed esenti da sporco, unto e materiali contaminanti.
- Su legno nuovo, applicare una mano preliminare di impregnante VERNOCOL.
- Su legno già verniciato, rimuovere le vernici non bene aderenti e carteggiare con carta abrasiva a grana fine.

WoodLine - varnish

One component polyurethane water-borne protective varnish, for interior and exterior use, with outstanding flexibility and resistance to UV rays and weathering.

HYDROLUX has a high scratch resistance and surface hardness, it is not yellowing and easy cleanable. It is odorless and therefore particularly suitable for indoor use and not well aired rooms.

HYDROLUX is particularly recommended for furniture, parquet floors, and any wood application.

Pack sizes

- 0.750 L – 5 L

V.O.C.

- <60 g/l

Specific gravity

- $1.020 \pm 0.030 \text{ kg/dm}^3$

Finish

- Glossy or flat

Colour range

- transparent

Practical coverage

- $10 \div 12 \text{ m}^2/\text{l}$

Practical consumption

- $70 \div 100 \text{ ml/m}^2$

Thinner

- water

Application

- Air spray
- Roller, brush

Surface preparation

- Be sure surface is clean, dry and free of oil, grease, natural resins and any other contaminant.
- On new timber, apply a preliminary coat of VERNOCOL.
- On previously coated timber, remove any poorly adhering coating and sandpaper with fine sandpaper.

Numero delle mani

- Almeno due

Condizioni di applicazione

- Temperatura: 10-40°C
- Umidità relativa <80%

Dati per l'applicazione**Spruzzo ad aria**

- | | | |
|-------------------|---------|-------|
| • Diluizione | 5÷10 | % v/v |
| • Diametro ugello | 1.4÷1.7 | mm |
| • pressione | 3÷4 | atm |

Rullo, pennello

- | | | |
|--------------|-----|-------|
| • Diluizione | 0÷5 | % v/v |
|--------------|-----|-------|

Tempi di indurimento a 20°C – 50% U.R.

- | | |
|-----------------|-------|
| • al tatto | 1-2 h |
| • ripitturabile | 24 h |

Finiture consigliate

- nessuna

Lavaggio delle attrezzature

- acqua immediatamente dopo l'uso

Durata a magazzino

- 12 mesi, con T max di 40°C, in latta sigillata, al coperto e al riparo dal gelo.

Coats

- Two at least

Environmental conditions

- Temperature: 50-120°F
- Relative humidity <80%

Application data**Air spray**

- | | | |
|---------------------|---------|-------|
| • Thinning | 5÷10 | % v/v |
| • Nozzle's diameter | 1.4÷1.7 | mm |
| • Pressure | 3÷4 | atm |

Roller, brush

- | | | |
|------------|-----|-------|
| • Thinning | 0÷5 | % v/v |
|------------|-----|-------|

Drying times at 68°F – 50% R.H.

- | | |
|-------------|-------|
| • to touch | 1-2 h |
| • to recoat | 24 h |

Recommended finish

- none

Cleaning up

- water immediately after use

Shelf life

- 12 months, with T max of 100°F, in sealed drum, indoors and protected against freeze.

Poiché le condizioni di impiego dei nostri materiali non sono sotto il nostro controllo, non possiamo che garantire la qualità dei prodotti, quindi non ci assumiamo alcuna responsabilità circa l'uso che dei medesimi viene fatto e circa qualsivoglia danno diretto o indiretto possa derivare a chiunque dal loro impiego. G.FARBEX non dà alcuna garanzia, implicita o esplicita, salvo specifica pattuizione scritta fra le parti.

This product data sheet is based on data believed to be reliable, and are intended for use by personnel having skill and know-how, at their own risk and in accordance with current industry practice and normal operating conditions. Variation in operating conditions and procedures may cause unsatisfactory results. Since we have no control over the conditions of service, we expressly disclaim any responsibility for the results obtained from the use of this product or for any consequential or incidental effects of any kind.